

PS5700 from SILEX

70 Shore A Fluorosilicone Rubber

Characteristics

PS5700 fluorosilicone rubber is noted for its good mechanical properties and resistance to harsh organic solvents and petroleum based fluids.

Due to the high green strength of this product, it can be used to make complex moulded or extruded parts. The vulcanising characteristics make it possible to achieve short cycle times in the production of rubber mouldings by compression, transfer and injection moulding.

Physical Characteristics

- Excellent fluid resistance
- Good compression set

Processing Characteristics

- Excellent handling when mixing
- Excellent moulding qualities

Special Characteristics

PS5700 fluorosilicone rubber from Silex Ltd offers superior resistance to organic solvents and petroleum based fluids. PS5700 readily accepts filler, additives and colours to modify its physical properties and appearance. While most fluorosilicone rubbers are sticky, PS5700 offers superior handling with improved mill and mould release, making it suitable for moulded, extruded or calendared applications.

Processing

Recommended Curing Agent Levels:

- 1.5 parts: 2,4-dichlorobenzoyl peroxide (50% active in silicone paste) per 100 parts of base.
- 0.7 parts: dicumyl peroxide (98% active) per 100 parts of base.
- 0.6 parts: 2,5-di(t-butylperoxy) -2,5-dimethylhexane (100% active) per 100 parts of base.
- 1.0 part: dibenzoyl peroxide (50% active in silicone paste) per 100 parts of base.

Properties

Typical property values are not intended for use in the preparation of specifications. Please contact Silex Ltd for assistance before writing specifications on this product.

Storage

PS5700 has a shelf life of at least 12 months when stored below 32°C in the tightly closed original container. Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. However, the properties relevant for the intended use must be verified for quality assurance reasons.

Product Data*

Property	Test Method	Value
		PS5700
Appearance	WSTM-1279	Off white
Density (g/cm ³), 25°C	ASTM D792	1.50
Hardness, Shore A	ASTM D2240	70
Tensile Strength (N/mm ²)	ASTM D412	5.86
Elongation at Break (%)	ASTM D412	150
Tear Strength, die B (N/mm)	ASTM D624	17.5
Compression Set, 22 h at 175°C (%)	ASTM D395	18
Brittle point (°C)	ASTM D2137	-60

*Properties obtained by adding 0.6 parts: 2,5-Di(t-butylperoxy)-2,5-dimethylhexane (100% active) per 100 parts of base; press cured 10 min/177°C and post cured 4 h/200°C.

S I L E X

S I L I C O N E S

Additonal Information

PS5700 fluorosilicone rubber is available in 1 kg boxes up to 540 kg boxes. Orders may be placed directly to:

Silex Ltd
Units 4 & 5 Broxhead Trading Estate
Lindford, Nr. Bordon
Hampshire, GU35 0NY

To speak with a technical representative or for information on other Silex products call 0044 1420 488042.

Safety information

For specific information regarding the safe handling of this material, please refer to the Material Safety Data Sheet.

Because we cannot foresee the varied conditions under which this information and our materials may be used, we do not guarantee the applicability or accuracy of this information or the suitability of our materials in any specific situation. Samples are provided and users should make their own tests to determine the suitability of our materials for their specific purposes. These materials are provided without warranty, either expressed or implied, of fitness for a specific purpose and nothing herein shall be construed as a recommendation for uses, which infringe valid patents, or as extending a license under valid patents.

For technical, quality, or product safety questions, please contact:

SILEX LTD
Units 4 & 5 Broxhead Trading Estate
Lindford, Bordon, Hampshire, GU35 0NY
TEL: 0044 1420 488042
FAX: 0044 1420 489274
E-mail: info@silex.co.uk