

Technical Data Sheet

ACRYLIC TISSUE TAPE - PH 8441



Material

Acrylic Tissue Tape



Available Thicknesses

115 micron

Product Overview

- Liner 80g Brown siliconized release paper
- Carrier 13G Tissue
- Adhesive Acrylic based with 45gsm on both open and closed sides
- Total thickness 115 micron

Performance Properties

- Peel adhesion to steel (24-hour dwell) protected 650 N/M
- Shear adhesion to steel: protected 50 hours open 50 hours
- Service temperature range: 10°C to 180°C
- Recommended application temperature range: 5°C to 60°C
- Shelf life: Recommended 12 months from supply

Food Contact Information

Based on supplier information the raw materials used in producing the adhesive tape conform to the compositional requirements of FDA 175.105 for indirect food contact. Additional to this compliance there should also be a functional barrier between adhesive and the food. Such functional barrier and determination of suitability are the responsibility of the customer.

Availabilities

Widths: 3mm, 6mm, 9mm, 12mm, 25mm, 50mm, 1000mm (other widths available)
Lengths: 10M, 25M, 50M, 100M, 250M (other lengths available)

This information and our technical advice, whether verbal, in writing or by way of trials, is given in good faith but without warranty. This also applies where proprietary rights are involved. Our advice does not release you from the obligations to check its validity and to test our products as to their suitability for their intended use. The storage, application and use of our products are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale. The information contained within this data sheet is subject to change without notice. Issue date 01.01.2019.

SILEX SILICONES LTD

Silex Ltd, Unit 10, Oakhanger Farm Business Park, Oakhanger, Bordon, Hampshire, GU35 9JA. Tel 00 44 1420 470360, Fax 00 44 1420 472802

E-Mail: sales@silex.co.uk, Website: www.silex.co.uk, Registered company number: 1951973. Place of registration: England & Wales. Directors: K Soudah, S.J. Fearn, P Millson, Ray Soudah